


PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: B01D 19/00, C01B 31/00	A1	(11) International Publication Number: WO 97/32647 (43) International Publication Date: 12 September 1997 (12.09.97)
(21) International Application Number: PCT/US97/04113 (22) International Filing Date: 6 March 1997 (06.03.97) (30) Priority Data: 60/012,930 6 March 1996 (06.03.96) US 08/816,403 5 March 1997 (05.03.97) US (71) Applicant: THE UNITED STATES OF AMERICA, represented by THE ADMINISTRATOR OF THE NATIONAL AERONAUTICS AND SPACE ADMINISTRATION (NASA) [US/US]; Washington, DC 20546 (US). (72) Inventors: RIVERS, Horace, Kevin; 42 Lakefield Crossing, Hampton, VA 23681-0001 (US). RANSONE, Philip, Owen; 1325 Laurens, Gloucester, VA 23062 (US). NORTHAM, George, Burton; 24481 Miller Lane, Carrollton, VA 23314 (US). (74) Agent: HELFRICH, George, F.; NASA Langley Research Center, 3 Langley Boulevard, Mail Stop 212, Hampton, VA 23665 (US).		(81) Designated States: CA, JP, KR, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: CHOPPED-FIBER COMPOSITE PISTON ARCHITECTURES		
(57) Abstract <p>A three-dimensional piston molding is fabricated from a mixture of chopped, carbon tow filaments of variable length, which are prepregged with carbonaceous organic resins and/or pitches and molded by conventional molding processes into near net shape, to form a carbon-fiber reinforced organic-matrix composite part. Continuous reinforcement in the form of carbon-carbon composite tapes or pieces of fabric can be also laid in the mold before or during the charging of the mold with the chopped-fiber mixture, to enhance the strength in the crown (21) and wrist-pin areas (23). The molded chopped-fiber reinforced organic-matrix composite parts are then pyrolyzed in an inert atmosphere, to convert the organic matrix materials to carbon. These pyrolyzed parts are then densified by reimpregnation with resins or pitches, which are subsequently carbonized. Densification is also accomplished by direct infiltration with carbon by vapor deposition processes. Once the desired density has been achieved, the piston molds are machined to final piston dimensions, and piston ring grooves are added. To prevent oxidation and/or to seal the piston surface or near surface, the chopped-fiber piston (20) is coated with ceramic and/or metallic sealants; and/or coated with a catalyst.</p> 		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LJ	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

-1-

CHOPPED-FIBER COMPOSITE PISTON ARCHITECTURES

Claim of Benefit of Provisional Application.

- 5 Pursuant to 35 U.S.C. §119, the benefit of priority from
provisional application 60/012,930, with a filing date of March 6, 1996,
is claimed for this non-provisional application.

Origin of the Invention

10

The invention described herein was made by employees of the
United States Government and may be manufactured and used by or for
the Government for governmental purposes without the payment of any
royalties thereon or therefor.

15

Background of the Invention1. Field of the Invention

- 20 This invention relates to lightweight piston design, and more
specifically to improved structures for a carbon-carbon composite piston.

2. Description of the Related Art

- 25 Internal combustion reciprocating engines and compressors used
for aerospace, military, and transportation applications must be
lightweight and capable of operating at elevated temperatures and
pressures. Current state-of-the-art of piston manufacture employs
aluminum alloys and steel because pistons composed of these materials

-2-

can withstand the relatively high temperatures and pressures associated with operation of an internal combustion engine or compressor. However, engine and compressor pistons manufactured of steel and/or aluminum alloys are very heavy.

- 5 Aside from weight concerns, one disadvantage of aluminum alloy pistons is an inherent, relatively high coefficient of thermal expansion, which necessitates larger clearances between an aluminum alloy piston and an engine cylinder liner, to allow for expansion of the aluminum alloy piston during engine warm-up. Even at operating temperature, a
- 10 clearance has to be maintained to allow for further piston expansion in the event that the engine experiences overheating due to intermittent, heavy loading or accidental loss of coolant. In order to seal the gap between an aluminum alloy piston and engine cylinder liner, the piston must be fitted with a plurality of piston rings which effectively seal the
- 15 gap.

- Another drawback associated with operation of an aluminum alloy piston at operating temperatures above 500 degrees Fahrenheit (°F), is a dramatic decrease in mechanical strength. This strength loss precludes locating the uppermost compression piston ring close to the top or crown
- 20 of the piston and may result in piston failure. As a result of the restriction on placing the uppermost piston compression ring close to the piston crown, a crevice between the piston crown and the uppermost piston compression ring is created. Because fuel mixture which reaches this crevice does not burn completely, the crevice contributes to
- 25 atmospheric pollution and reduces fuel efficiency. Steel pistons have sufficient strength at higher temperatures but are excessively heavy.

Yet another disadvantage of aluminum alloy pistons also results from the thermal expansive properties of the alloy. As undersized aluminum alloy pistons "rock" inside the cylinder chamber, they can be

-3-

noisy until such time as they have sufficiently expanded in size to better fit the cylinder chamber dimensions. Carbon-carbon composite pistons have greater dimensional stability, i.e. are less thermally expansive and therefore consistently retain their dimensions, hence producing no engine knocking during cold operation.

In a recent development, internal combustion engine and/or compressor pistons are fabricated from carbon-carbon composite materials to reduce engine weight, improve engine efficiency, reduce hydrocarbon emissions, potentially eliminate the need for piston rings, and produce a less noisy engine. These carbon-carbon composite pistons retain their strength under operating conditions which exceed 1200 °F, and are lighter than either steel or aluminum alloy pistons.

Carbon-carbon composite pistons, however, are fabricated by manually laying-up and molding prepregged fabrics, tapes, or felted preforms. Such processes are labor-intensive and, therefore, expensive. These carbon-carbon composite pistons also have reduced interlaminar strength and exhibit anisotropy in their mechanical properties, thermal expansion, and thermal conductivity.

Summary of the Invention

Accordingly an object of this invention is to reduce the weight of an internal combustion reciprocating engine and/or compressor.

It is another object of the present invention to provide an engine and/or compressor piston with adequate mechanical strength during high engine operating temperatures, resulting in lower distortion and higher dimensional stability.

Another object of the present invention is to provide an engine and/or compressor piston which eliminates low interlaminar strength.

-4-

Yet another object of the present invention is to provide an engine and/or compressor piston which can be cheaply mass produced.

Still another object of the present invention is to provide an engine and/or compressor piston with isotropic mechanical and physical
5 properties as well as thermal expansion and thermal conductivity.

It is yet another object of the present invention to provide an engine and/or compressor piston which can be ringless.

It is a further object of the present invention to provide an engine and/or compressor piston which improves engine operating efficiency.

10 It is an additional object of the present invention to provide an engine and/or compressor piston which operates more quietly.

It is a further object of the present invention to provide an engine and/or compressor piston which reduces the emission of hydrocarbons during operation by reducing the crevice volume.

15 According to the present invention, the foregoing and additional objects are attained by fabricating a three-dimensional piston molding from a mixture of chopped, carbon tow filaments of uniform or variable length, which are prepregged with carbonaceous organic resins and/or pitches and molded by conventional molding processes into a near net
20 shape, to form a carbon-fiber reinforced organic-matrix composite part. Continuous reinforcement in the form of carbon-carbon composite tapes or pieces of fabric can be also laid in the mold before or during the charging of the mold with the chopped-fiber mixture, to enhance the strength in the crown and wrist-pin areas. The molded chopped-fiber
25 reinforced organic-matrix composite parts are then pyrolyzed in an inert atmosphere, to convert the organic matrix materials to carbon. These pyrolyzed parts are then densified by reimpregnation with resins or pitches, which are subsequently carbonized. Densification is also accomplished by direct infiltration with carbon by vapor deposition

-5-

processes. Once the desired density has been achieved, the piston molds are machined to final piston dimensions, and piston ring grooves are added. To prevent oxidation and/or to seal the piston surface or near surface, the chopped-fiber piston is coated with ceramic and/or metallic sealants; and/or coated with a catalyst.

Like conventional carbon-carbon composite pistons, chopped-fiber pistons are lighter than aluminum alloy pistons. Unlike conventional carbon-carbon composite pistons, however, chopped-fiber pistons exhibit less strength than aluminum alloy pistons at room temperature.

However, chopped-fiber pistons retain their strength at higher operating temperatures while aluminum alloy pistons experience a dramatic loss of strength. Chopped-fiber is molded into a better, i.e. more perfect, net shape mold which requires less finishing than for a cast aluminum alloy piston.

Brief Description of the Drawings

FIG. 1 is an illustration of a prior art knitted carbon fiber structure engine piston; and

FIG. 2 is an illustration of a near net-shaped chopped-fiber piston.

Detailed Description of the Invention

Carbon-carbon composite materials, as used herein, refers to a predominantly carbon matrix material reinforced with predominantly carbon fibers. The properties of these materials may be tailored to produce any desired mechanical and physical properties by preferred orientation of the continuous or staple fibers in the composite materials; and/or by the selection of additives; and/or by thermal treatment of the

-6-

fibers and matrix before, during, or after fabrication. Carbon-carbon composite materials may be cast or molded, and are machineable. The surface or near-surface material can also be treated and/or coated with oxidation protection or sealing materials, or with catalytic materials such as nickel.

The present invention is an improvement in the manufacture and structure of a lightweight carbon-carbon composite engine piston for use in internal combustion engines and/or compressors. U.S. Patent No. 4,909,133 by Taylor et al. discloses the use of knitted or warp interlock preforms which are embedded in the composite matrix so as to comprise structural components of the completed piston. The lightweight piston architecture of Taylor et al. is shown as Figure 1 which depicts a carbon-carbon composite engine piston 10 which has a knitted or woven carbon fiber structure 12 which is selectively reinforced with directionally-oriented carbon fibers at the crown 13 and adjacent to the wrist pin boss 14.

The improvement of the present invention comprehends fabricating carbon-carbon composite pistons from a near net-shaped molding composed of chopped carbon tow bundles, i.e. "chopped fiber." These tow bundles consist of between 2,000 to 3,000 individual carbon filaments wrapped about one another with a common axis, such that the tow bundle has a diameter of approximately 0.5 mm. The chopped fibers should not exceed 0.5 inches in length, which can be of uniform or variable length. The preferred embodiment employs chopped fibers of variable length. Additives and/or fillers with properties tailored to yield desirable thermal and/or structural properties may be added to the chopped-fiber matrix before it is charged into the mold.

Refer to Figure 2 which depicts a chopped fiber piston 20. The improved architecture of the present was created by process which

-7-

5 began by cutting or chopping carbon tow bundles into uniform or variable lengths not to exceed 0.5 inches. These chopped-fibers were then blended with carbonaceous resins, i.e. the matrix resin, and any desired additives and/or fillers. Chopping carbon tow bundles and blending them with resin can be done separately, in individual steps, or in a single step by any known chopping or blending means. Mixing the chopped fibers, matrix resin, and additives or fillers in a blender is the preferred single-step means.

10 The chopped fiber-resin mixture was then charged in a near-net shape mold by conventional molding techniques.

Continuous reinforcement in the crown 21 and wrist-pin area 23, where higher strengths are required, can be incorporated into the molding by laying continuous tape or fabric pieces into the mold at desired locations and adding the chopped-fiber mixture as required. Continuous reinforcement may be applied first, last, or alternately, along with the chopped-fiber mixture.

The near net-shape molding was then heated to cure the matrix resin. Typically, the molding curing temperature ranges between 300 and 400 degrees F.

20 The cured near-net shaped molding was then removed from its mold and pyrolyzed to a temperature of 900 degrees Celsius (°C) in an inert-atmosphere furnace, to convert the organic matrix material into carbon. A pyrolyzing temperature of 2700 °C may be required if any graphitizable constituents were included in the matrix precursor resins as an additive, to form graphite in situ or if graphitization of the fibers is desirable.

The density of the pyrolyzed, chopped-fiber molding is increased, as required, by one or more cycles of resin reimpregnation and carbonization as described in U.S. Patent No. 4,683,809 (Taylor).

-8-

Alternately, densification is effected by direct deposition of carbon in the pores of the chopped fiber molding using chemical vapor deposition processes which are known in the art.

- Once the desired densification was achieved, all densified chopped
- 5 fiber moldings were then machined and burnished to final dimensions, to produce a chopped-fiber piston 20. If desired or required, grooves (not shown) for piston rings (not shown) may be machined into the completed chopped fiber piston 20. Typically, diamond impregnated grinding tools are used for machining, as single-point cutting tools tend to tear out
- 10 fibers and chip out bits of the matrix leaving an unacceptable surface. Burnishing the surfaces of the piston skirt, ring groove, and wrist pin hole to the final critical dimensions is desirable, to minimize or eliminate the wear which can be experienced when carbon-carbon surfaces initially contact other surfaces.
- 15 The piston crown, ring groove, and piston skirt surfaces are coated with a ceramic or with a metallic coating, as required, to seal the surface, provide some protection against oxidation, and/or provide better tribological properties. Catalytic coatings, such as nickel, also may be applied to the crown surfaces 22 of the finished chopped-fiber piston.
- 20 The invention can be practiced in other manners than are described herein without departing from the spirit and the scope of the appended claims.

What is claimed is:

-9-

Claims:

1. A process for fabricating carbon fiber pistons, which comprises:
 - 5 (a) cutting prepregged carbon tow bundles into chopped fibers which are defined by a length;
 - (b) mixing said chopped fibers with a carbonaceous resin, to form a chopped-fiber mixture;
 - (c) introducing additives or fillers into the chopped-fiber
 - 10 mixture, to impart desired thermal and structural properties to said chopped-fiber mixture;
 - (d) charging the chopped-fiber mixture containing additives or fillers into a mold assembly, to form a chopped-fiber molding;
 - (e) inserting continuous reinforcement where higher mechanical
 - 15 strengths are desired;
 - (f) heating the chopped-fiber molding, to cure the carbonaceous resin in the prepregged carbon tow bundles;
 - (g) pyrolyzing the heated chopped-fiber molding, to carbonize the heated chopped-fiber molding;
 - 20 (h) re-impregnating the heated chopped-fiber molding with additional carbonaceous resin;
 - (i) re-pyrolyzing the re-impregnated carbonized chopped-fiber molding, to further densify the chopped-fiber molding; and
 - (j) machining the further densified chopped-fiber molding to
 - 25 final dimensions, producing a chopped-fiber piston with a crown and complete piston skirt surfaces.
2. The process for fabricating carbon fiber pistons of claim 1, wherein the length of the chopped fibers does not exceed 0.50 inches.

-10-

3. The process for fabricating carbon fiber pistons of claim 1,
wherein the length of the chopped fibers is variable.
4. The process for fabricating carbon fiber pistons of claim 1,
5 wherein the length of the chopped fibers is uniform.
5. The process for fabricating carbon fiber pistons of claim 1,
wherein mixing is accomplished by blending.
- 10 6. The process for fabricating carbon fiber pistons of claim 1,
wherein the continuous reinforcement is a carbon-carbon composite tape.
7. The process for fabricating carbon fiber pistons of claim 1,
wherein the reinforcement is a piece of carbon-carbon composite fabric.
15
8. The process for fabricating carbon fiber pistons of claim 1,
wherein the chopped-fiber molding is heated to a temperature between
about 300 and 400 degrees Fahrenheit, to cure the carbonaceous resin.
- 20 9. The process for fabricating carbon fiber pistons of claim 1,
wherein the heated chopped-fiber molding is pyrolyzed at a temperature
of approximately 900 degrees Centigrade, to carbonize the carbonaceous
resin.
- 25 10. The process for fabricating carbon fiber pistons of claim 1,
wherein the chopped-fiber molding is pyrolyzed at a temperature of
approximately 2700 degrees Centigrade, to form in situ graphite.

-11-

11. The process for fabricating carbon fiber pistons of claim 1, further comprising the step of:
machining ring grooves into the machined chopped-fiber piston.

5 12. The process for fabricating carbon fiber pistons of claim 1, further comprising the step of:
coating the crown and piston skirt surface of the machined chopped-fiber piston with a sealant for oxidation protection.

10 13. The process for fabricating carbon fiber pistons of claim 12, wherein the sealant is a ceramic coating.

14. The process for fabricating carbon fiber pistons of claim 12, wherein the sealant is a metallic coating.

15

15. The process for fabricating carbon fiber pistons of claim 1, further comprising the step of:
coating the crown surface of the machined chopped-fiber piston with a catalytic coating.

20

16. The process for fabricating carbon fiber pistons of claim 15, wherein the catalytic coating is nickel.

17. An improved carbon fiber piston for an internal combustion
25 engine or compressor which is fabricated by the process of claim 1.

18. An improved carbon fiber piston for an internal combustion engine or compressor which is fabricated by the process of claim 11.

-12-

19. An improved carbon fiber piston for an internal combustion engine or compressor which is fabricated by the process of claim 12.

20. An improved carbon fiber piston for an internal combustion
5 engine or compressor which is fabricated by the process of claim 15.

FIG. 1





FIG. 2



INTERNATIONAL SEARCH REPORT

International application No.
PCT/US97/04113

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) :B01D 19/00; C01B 31/00

US CL :92/248; 264/29.5

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 92/172,248; 123/193.6; 264/29.5

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched
NONE

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

APS

search terms: piston, carbon, fiber?, filament?, impregnate?

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
-	-	-
A	US 4,683,809 A (TAYLOR) 04 August 1987, entire document.	1-20
A	US 4,694,735 A (TATEMATSU et al.) 22 September 1987, entire document.	1-20
A	US 5,101,556 A (FLUGA et al.) 07 April 1992, entire document.	1-20
A,P	US 5,525,276 A (OKUYAMA et al.) 11 June 1996, entire document.	1-20

☐ Further documents are listed in the continuation of Box C.

☐ See patent family annex.

Special categories of cited documents:	
A document defining the general state of the art which is not considered to be of particular relevance	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
E earlier document published on or after the international filing date	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
L document which may throw doubt on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
O document referring to an oral disclosure, use, exhibition or other means	*A* document member of the same patent family
P document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

11 JUNE 1997

Date of mailing of the international search report

09 JUL 1997

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Authorized officer

CHRISTOPHER A. FIORILLA

Facsimile No. (703) 305-3230

Telephone No. (703) 308-0674